arXiv:1606.09283v1 [cond-mat.str-el] 29 Jun 2016

Shapiro Spikes and Negative Mobility for Skyrmion Motion on Quasi-One Dimensional Periodic Substrates

C. Reichhardt and C. J. Olson Reichhardt
Theoretical Division and Center for Nonlinear Studies,
Los Alamos National Laboratory, Los Alamos, New Mexico 87545, USA
(Dated: July 1, 2016)

Using a simple numerical model of skyrmions in a two-dimensional system interacting with a quasi-one dimensional periodic substrate under combined dc and ac drives where the dc drive is applied perpendicular to the substrate periodicity, we show that a rich variety of novel phase locking dynamics can occur due to the influence of the Magnus term on the skyrmion dynamics. Instead of Shapiro steps, the velocity response in the direction of the dc drive exhibits a series of spikes, including extended dc drive intervals over which the skyrmions move in the direction opposite to the dc drive, producing negative mobility. There are also specific dc drive values at which the skyrmions move exactly perpendicular to the dc drive direction, giving a condition of absolute transverse mobility.

PACS numbers: 75.70.Kw,75.70.Ak,75.85.+t,75.25.-j

When an overdamped particle is driven by a combined dc and ac drive over a periodic substrate, a series of steps, called Shapiro steps [1], appear in the velocity response over fixed dc drive intervals due to phase locking between the ac driving frequency and the oscillatory frequency of the particle motion induced by the substrate periodicity. Phase locking of this type occurs for dc plus ac driven Josephson junction arrays [2], sliding charge density waves [3], vortices in type-II superconductors [4–6] or colloids [7] moving over periodic pinning arrays, frictional systems [8], and numerous other nonlinear systems in which there are two coupled competing frequencies [9–11]. In a two dimensional (2D) overdamped system with a quasi-one-dimensional (q1D) substrate, Shapiro steps only occur when the dc and ac drives are both applied parallel to the substrate periodicity direction, since the pinning does not induce a periodic modulation of the particle motion for perpendicular driving. In some systems, additional non-dissipative terms can be relevant to the particle dynamics, such as a Magnus force which generates a particle velocity component that is perpendicular to the net applied force on the particle. Magnus effects are known to be important for skyrmions in chiral magnets, where the ratio of the Magnus term to the damping term can be ten or higher [12–17]. Skyrmions can be set into motion by an applied spin-polarized current, and the Magnus term has been shown to strongly affect the interaction of the moving skyrmions with pinning sites, leading to reduced depinning thresholds [14–16, 18, 19], a drive dependent skyrmion Hall angle [19–22], and skyrmion speed up effects [20, 21].

Recent studies of skyrmions driven over a periodic q1D substrate by a dc drive that is parallel to the substrate periodicity direction combined with a perpendicular ac drive showed that a new class of Magnus-induced Shapiro steps arises due to an effective coupling by the Magnus term of the perpendicular and parallel particle motion, whereas in the overdamped limit no Shapiro steps occur for this drive configuration [23]. Here we examine skyrmions confined to a 2D plane containing a q1D periodic substrate and moving under the influence of a dc drive applied *perpendicular* to the substrate periodicity direction along with a parallel or perpendicular ac drive, and we find that a rich variety of dynamical phases can occur. Instead of Shapiro steps, the particle velocity response in the dc drive direction exhibits what we call Shapiro spikes where the slope of the velocity-force curve locks to a constant value over a range of dc driving forces. One of the most remarkable features of this system is that there are also a series of extended dc drive regions where the particle motion is in the direction *opposite* to the dc drive, known as negative mobility [24–26]. It is even possible for the particle motion at some drives to be exactly perpendicular to the dc drive direction, creating a condition of absolute transverse mobility [27]. Negative mobility effects have been observed in overdamped systems but generally require more complicated substrates, thermal fluctuations, many-particle collective effects, or the application of multiple ac drives, whereas in the skyrmion system, negative mobility arises for a much simpler set of conditions. We map the evolution of the dynamic phases as a function of ac drive amplitude and the ratio of the Magnus to the damping term. In addition to their interest as signatures of a new dynamical system, these results could be important in providing a new way to precisely control the direction of motion of skyrmions in order to realize skyrmion-based memory or logic devices [28].

Simulation– We model a 2D system with periodic boundary conditions in the x and y directions containing a q1D substrate and a skyrmion treated with a particle-based model that has previously been used to examine driven skyrmion motion in random[18, 19], 2D periodic [21], and 1D periodic substrates [23, 29]. The skyrmion dynamics are determined using the following equation of



FIG. 1: (a) The average skyrmion velocity $V_{||}$ (blue) and $V_\perp$ (red) vs $F^\perp_{dc}$ for a system with pinning strength $A_p = 1.0$ and perpendicular ac drive $F^\perp_{ac} = 0.325$ at different ratios α_m/α_d of the Magnus to dissipative terms. Solid lines: $\alpha_m/\alpha_d = 9.96$; dashed lines: $\alpha_m/\alpha_d = 0$. For $\alpha_m/\alpha_d = 9.96$, there are Shapiro steps in $V_{||}$ and spikes in $V_\perp$, along with intervals in which $V_\perp < 0$. (b) The same for $\alpha_m/\alpha_d = 3.219$ (solid lines) and $\alpha_m/\alpha_d = 0$ (dashed lines).

motion:

$$\alpha_d \mathbf{v}_i + \alpha_m \hat{z} \times \mathbf{v}_i = \mathbf{F}^{sp}_i + \mathbf{F}_{dc} + \mathbf{F}_{ac}, \tag{1}$$

where the skyrmion velocity is $\mathbf{v}_i = d\mathbf{r}_i/dt$. On the left hand side, α_d gives the strength of the damping term, which aligns the skyrmion velocity in the direction of the net external forces, while α_m is the Magnus term, which rotates the velocity in the direction perpendicular to the net external forces. For varied ratios of α_m/α_d we impose the constraint $\alpha_d^2 + \alpha_m^2 = 1$. The force from the substrate is $\mathbf{F}^{sp}_i = \nabla U(x_i)\hat{\mathbf{x}}$ where $U(x) = U_o \cos(2\pi x/a)$ and a is the substrate lattice constant. The substrate strength is defined to be $A_p \equiv 2\pi U_0/a$. The dc drive $\mathbf{F}_{dc} = F^\perp_{dc}\hat{\mathbf{y}}$ is applied perpendicular to the substrate periodicity direction, while the ac driving force $\mathbf{F}_{ac} = F^{||}_{ac}\hat{\mathbf{x}}$ or $\mathbf{F}_{ac} = F^\perp_{ac}\hat{\mathbf{y}}$ is applied either parallel or perpendicular to the substrate periodicity direction, respectively. We characterize the system by measuring the velocity response $V_{||} = 2\pi\langle V_x\rangle/\omega a$ parallel to the substrate periodicity and $V_\perp = 2\pi\langle V_y\rangle/\omega a$ perpendicular to the substrate periodicity, so that on a Shapiro step the velocity is integer valued with $V_{||} = n$ or $V_\perp = n$, allowing us to identify the step number n.

Results and Discussion— In Fig. 1(a) we plot $V_{||}$ and $V_\perp$ versus $F^\perp_{dc}$ for a system with $A_p = 1.0$, $\alpha_m/\alpha_d = 9.96$, and $F^\perp_{ac} = 0.325$. The dashed lines show the average velocities in the overdamped limit of $\alpha_m/\alpha_d = 0$, where the particles simply slide along the y-direction with an Ohmic response and phase locking does not occur. When the Magnus term is finite, $V_{||}$ shows a series of phase-locked Shapiro steps, while $V_\perp$ shows a completely different response consisting of spike like features. On each phase-locked step in $V_{||}$, the slope of $V_\perp$ is constant. The most remarkable feature in $V_\perp$ is that there are four extended intervals of $F^\perp_{dc}$ over which $V_\perp < 0$, indicating that the particle is moving in the *opposite* direction to the applied dc drive, a phenomenon known as negative mobility [25, 26]. On a given step, $V_\perp$ can grow from negative values to positive values, passing through a point at which $V_{||}$ is finite but $V_\perp = 0$, indicating that particle is moving exactly perpendicular to the applied dc drive in a phenomenon known as absolute transverse mobility [27]. At higher values of $F^\perp_{dc}$, the negative mobility regions are lost and the minimum value of $V_\perp$ at the bottom of each spike increases with increasing $F^\perp_{dc}$. At the top of the $V_\perp$ spikes, the particle velocity in the dc drive direction is higher than it would be in an overdamped system, which is an example of a pinning-induced speed up effect [20, 21]. After each spike, $V_\perp$ decreases with with increasing $F^\perp_{dc}$, which is an example of negative differential conductivity. In Fig. 1(b) we show that for $\alpha_m/\alpha_d = 3.219$, there are still spikes in $V_\perp$; however, the regions of negative mobility are lost. As α_m/α_d is further reduced, $V_\perp$ gradually becomes smoother and approaches the dashed line, which indicates the response in the overdamped limit.

From the dynamics in Fig. 1(a) we define six different regimes for the particle motion. Region I is a phase locked state in which the particle moves in a periodic orbit with $V_\perp > 0$ and $V_{||} \geq 0$. In Fig. 2(a) we show the particle trajectory at $F^\perp_{dc} = 0.015$, corresponding to the $n = 0$ step where the particle orbit translates only along the y direction. Figure 2(d) illustrates the $n = 1$ step at $F^\perp_{dc} = 0.085$, where the particle moves in a periodic orbit that translates in both the positive x and y directions. Region II is a phase locked state in which the particle moves in the direction opposite to the dc driving force with $V_\perp < 0$, as shown in Fig. 2(b) for $F^\perp_{dc} = 0.055$ on the $n = 1$ step where the periodic particle orbit translates in the positive x and negative y directions. In Region III, which is also phase locked, the particle exhibits absolute transverse mobility and moves strictly in the positive x-direction with $V_\perp = 0$, as shown in Fig. 2(c) at $F^\perp_{dc} = 0.064815$. This corresponds to a skyrmion Hall angle of $\theta_{sk} = 90°$. Region IV is a non-phase locked state in which $V_\perp = 0$ while $V_{||}$ is positive. It occurs in the non-step regions where the particle does not follow a periodic orbit and does not translate along the y direction, such as near $F^\perp_{dc} = 0.04$ in Fig. 1(a). The absolute transverse mobility of Regions III and IV only occurs at specific values of $F^\perp_{dc}$, while the other phases span extended intervals of the dc driving force. Region V is a non-phase locked state where $V_\perp$ and $V_{||}$ are both positive but the particle does not form a periodic orbit, as illustrated in Fig. 2(e) at $F^\perp_{dc} = 0.095$. Finally, Region VI is a non-phase locked state in which $V_\perp < 0$ and $V_{||} > 0$, as shown in Fig. 2(f)



FIG. 2: Skyrmion location (dot) and trajectory (line) on a q1D periodic substrate potential for ac and dc drives both applied along the perpendicular or y direction for the system in Fig. 1(a) with $\alpha_m/\alpha_d = 9.96$. The lighter regions indicate the locations of the substrate minima. (a) $F^{\perp}_{dc} = 0.015$ along the $n = 0$ step. (b) $F^{\perp}_{dc} = 0.055$, showing a phase locked region with negative mobility where $V_{\perp} < 0$ and $V_{||} > 0$. (c) $F^{\perp}_{dc} = 0.064815$, where there is absolute transverse mobility with $V_{\perp} = 0$ and $V_{||} > 0$. (d) $F^{\perp}_{dc} = 0.085$ along the $n = 1$ step, where $V_{\perp}$ and $V_{||}$ are both positive. (e) $F^{\perp}_{dc} = 0.095$, where there is a non-phase locked region with $V_{\perp} > 0$ and $V_{||} > 0$. (f) $F^{\perp}_{dc} = 0.105$, where there is a non-phase locked region with negative mobility.

at $F^{\perp}_{dc} = 0.105$. We note that there can be smaller intervals outside of the integer phase locked steps over which the system can exhibit fractional phase locking, and that these fractional steps become more prominent for higher values of $F^{\perp}_{ac}$.

We next consider the case of a perpendicular dc drive and a parallel ac drive, as shown in Fig. 3(a) where we plot $V_{\perp}$ and $V_{||}$ vs $F^{\perp}_{dc}$ for a system with the same parameters as in Fig. 1(a) for $F^{||}_{ac} = 0.325$. Here, for $\alpha_m/\alpha_d = 9.96$, there are still steps in $V_{||}$ and spikes in



FIG. 3: (a) $V_{||}$ (blue) and $V_{\perp}$ (red) vs $F^{\perp}_{dc}$ for perpendicular dc driving and parallel ac driving at $F^{||}_{ac} = 0.325$. Solid lines: $\alpha_m/\alpha_d = 9.96$; dashed lines: $\alpha_m/\alpha_d = 0$. (b) The same for $F^{||}_{ac} = 2.35$, where there intervals in which $V_{\perp} < 0$. (c) $V_{||}$ (blue, green) and $V_{\perp}$ (red, purple) vs $F^{||}_{dc}$ for parallel dc driving and perpendicular ac driving at $F^{\perp}_{ac} = 0.325$ for $\alpha_m/\alpha_d = 9.96$ (blue and red), showing Shapiro steps, and for $\alpha_m/\alpha_d = 0$ (green and purple), where no Shapiro steps occur. (d) $V_{||}$ (blue, green) and $V_{\perp}$ (red, purple) vs $F^{||}_{dc}$ for parallel dc driving and parallel ac driving at $F^{||}_{ac} = 0.325$ for $\alpha_m/\alpha_d = 9.96$ (blue and red) and $\alpha_m/\alpha_d = 0$ (green and purple), showing Shapiro steps.

$V_{\perp}$; however, $V_{\perp} \geq 0$ for all $F^{\perp}_{dc}$. For the overdamped $\alpha_m/\alpha_d = 0$ case, $V_{||} = 0$ and $V_{\perp}$ increases linearly with increasing $F^{\perp}_{dc}$. In Fig. 3(b), for the same driving configuration at $F^{||}_{ac} = 2.35$, there are more steps in $V_{\perp}$ as well as regions in which $V_{\perp} < 0$, similar to the perpendicular ac driving case in Fig. 1(a). This shows that it is possible to observe negative mobility and spike features in $V_{\perp}$ whenever the dc drive is applied perpendicular to the substrate periodicity, regardless of the ac driving direction. The ac drive amplitudes at which the features appear are much lower for perpendicular ac driving than for parallel ac driving.

For comparison, Fig. 3(c) shows the results of applying a parallel dc drive $F^{||}_{d}$ and a perpendicular ac drive with $F^{\perp}_{ac} = 0.325$ at $\alpha_m/\alpha_d = 9.96$. Here, phase locking steps are present but the spikes associated with negative mobility are not. The curves for the overdamped case with $\alpha_m/\alpha_d = 0$ show that $V_{||}$ has a finite depinning threshold but no Shapiro steps, while $V_{\perp} = 0$ for all $F^{||}_{dc}$. In Fig. 3(d), both the ac and dc drives are parallel to the substrate periodicity with $F^{||}_{ac} = 0.325$. At $\alpha_m/\alpha_d = 9.96$, both $V_{||}$ and $V_{\perp}$ exhibit Shapiro steps, while in the overdamped limit with $\alpha_m/\alpha_d = 0$, $V_{||}$ contains Shapiro steps while $V_{\perp} = 0$. This shows that in the overdamped limit, Shapiro steps occur only when both the ac and dc driving are applied parallel to the sub-



FIG. 4: (a) Dynamic phase diagram for $F^{\perp}_{dc}$ vs $F^{\perp}_{ac}$ showing the locations of the $n = 0$, 1, and 2 steps (outlined in black) for $\alpha_m/\alpha_d = 9.96$. Green: phase locked regions with $V_{\perp} > 0$; white: unlocked regions with $V_{\perp} > 0$; orange: locked or unlocked regions with $V_{\perp} < 0$. Along the red lines, $V_{\perp} = 0$ and $V_{||} > 0$. (b) Dynamic phase diagram for $F^{\perp}_{dc}$ vs α_m/α_d at $F^{\perp}_{ac} = 0.325$. Colors are the same as in panel (a).

strate periodicity direction.

The negative mobility for perpendicular dc driving arises due to the combination of the Magnus term and the skyrmion-pinning interactions. Under a finite Magnus term, the dc drive generates an x direction force $F_x = F^{\perp}_{dc}\sin(\theta_{sk})$ on the skyrmion, where $\theta_{sk} = \tan^{-1}(\alpha_m/\alpha_d)$. In response, the substrate exerts an x direction force on the skyrmion that the Magnus term transforms into a y velocity component in the range $V_y = \pm A_p \sin(\theta_{sk})$. For certain intervals of $F^{\perp}_{dc}$, the $-y$ portion of the ac driving cycle synchronizes with the time at which the pinning force generates a $-y$ velocity component, resulting in a net negative value of $V_{\perp}$. Conversely, in other $F^{\perp}_{dc}$ intervals the $+y$ portion of the ac driving cycle synchronizes with the time at which the substrate generates a $+y$ velocity component, producing a speed up effect with enhanced positive $V_{\perp}$. Somewhere between these two intervals, $V_{\perp} = 0$ and absolute transverse mobility occurs. All of these effects become stronger for higher ac amplitude and larger ratios of α_m/α_d. A similar argument can be made for ac driving in the x-direction; however, the ac amplitude must be larger by a factor of approximately α_m/α_d, such as shown in Fig. 3(b), for effects of the same magnitude to occur, since for a parallel ac drive the y-velocity component is multiplied by a factor of $\cos(\theta_{sk})$ instead of $\sin(\theta_{sk})$.

In Fig. 4(a) we plot the evolution of the different regimes for the system in Fig. 1(a) as a function of $F^{\perp}_{dc}$ and $F^{\perp}_{ac}$, focusing only on the $n = 0$, 1, and 2 phase-locked regions. The width of the n-th phase locked step has the same J_n or Bessel function oscillating behavior predicted to occur for Shapiro steps [30]. The green shading denotes phase locked regimes with $V_{\perp} > 0$. White indicates unlocked regions with $V_{\perp} > 0$. The orange shading indicates phase locked and unlocked regions of negative mobility with $V_{\perp} < 0$, which form a series of triangles that overlap with the $n = 1$ and 2 steps. At the edges of these triangles, absolute transverse mobility with $V_{\perp} = 0$ and $V_{||} > 0$ occurs. We observe similar dynamic phases for steps with higher values of n. This result indicates that the direction of the skyrmion motion can be tuned by varying either the dc or ac perpendicular drives. In Fig. 4(b) we plot a dynamic phase diagram as a function of $F^{\perp}_{dc}$ and α_m/α_d at $F^{\perp}_{ac} = 0.325$. Here, for small α_m/α_d the skyrmion motion is locked in the perpendicular direction. Negative mobility occurs only for $\alpha_m/\alpha_d > 3.2$, and higher order steps emerge as α_m/α_d increases. Similar phase diagrams can be created for parallel ac driving; however, in this case, negative mobility does not occur until much higher ac driving amplitudes are applied. We also find that these effects are robust for multiple interacting skyrmions when the skyrmion-skyrmion interactions are modeled as a repulsive force.

Summary— We have shown that when a skyrmion obeying dynamics that are governed by both a Magnus and a dissipative term moves under combined ac and dc drives on a quasi-1D periodic substrate, a rich variety of phase locking phenomena can occur that are absent in the overdamped limit. When the dc drive is applied perpendicular to the substrate periodicity direction, for either parallel or perpendicular ac driving the perpendicular velocity response develops Shapiro steps, while the parallel velocity exhibits Shapiro spikes. We also observe extended dc drive intervals over which the skyrmion moves in the opposite direction to the dc drive, known as negative mobility, while for specific dc drive values we find absolute transverse mobility in which the skyrmion moves exactly transverse to the dc drive. When the dc drive is applied parallel to the substrate periodicity direction, the Shapiro spikes and negative mobility are absent, while in the overdamped limit Shapiro steps only occur when the dc and ac drives are both applied parallel to the substrate periodicity direction. The dynamics we observe should be realizable for skyrmions in chiral magnets interacting with quasi-1D substrates created using 1D thickness modulations or line pinning arrays, and open a new way to control skyrmion motion.

We gratefully acknowledge the support of the U.S. Department of Energy through the LANL/LDRD program for this work. This work was carried out under the auspices of the NNSA of the U.S. DoE at LANL under Contract No. DE-AC52-06NA25396 and through the LANL/LDRD program.

[1] S. Shapiro, Josephson currents in superconducting tunneling: the effect of microwaves and other observations, Phys. Rev. Lett. **11**, 80 (1963).
[2] S.P. Benz, M.S. Rzchowski, M. Tinkham, and C. J. Lobb, Fractional giant Shapiro steps and spatially correlated phase motion in 2D Josephson arrays, Phys. Rev. Lett.

64, 693 (1990).
[3] G. Grüner, The dynamics of charge-density waves, Rev. Mod. Phys. **60**, 1129 (1988).
[4] P. Martinoli, O. Daldini, C. Leemann, and B. Van den Brandt, Josephson oscillation of a moving vortex lattice, Phys. Rev. Lett. **36**, 382 (1976).
[5] L. Van Look, E. Rosseel, M.J. Van Bael, K. Temst, V.V. Moshchalkov, and Y. Bruynseraede, Shapiro steps in a superconducting film with an antidot lattice, Phys. Rev. B **60**, R6998(R) (1999).
[6] C. Reichhardt, R.T. Scalettar, G.T. Zimányi, and N. Grønbech-Jensen, Phase-locking of vortex lattices interacting with periodic pinning, Phys. Rev. B **61**, R11914(R) (2000).
[7] M.P.N. Juniper, A.V. Straube, R. Besseling, D.G.A.L. Aarts, and R.P.A. Dullens, Microscopic dynamics of synchronization in driven colloids, Nature Commun. **6**, 7187 (2015).
[8] O.M. Braun and Y.S. Kivshar, *The Frenkel-Kontorova Model: Concepts, Methods, and Applications* (Springer-Verlag, Berlin Heidelberg, 2010).
[9] E. Ott, *Chaos* (Cambridge, New York, 1993).
[10] P.T. Korda, M.B. Taylor, and D.G. Grier, Kinetically locked-In colloidal transport in an array of optical tweezers, Phys. Rev. Lett. **89**, 128301 (2002).
[11] C. Thomas and A.A. Middleton, Irrational mode locking in quasiperiodic systems, Phys. Rev. Lett. **98**, 148001 (2007).
[12] S. Mühlbauer, B. Binz, F. Jonietz, C. Pfleiderer, A. Rosch, A. Neubauer, R. Georgii, and P. Böni, Skyrmion lattice in a chiral magnet, Science **323**, 915 (2009).
[13] X.Z. Yu, Y. Onose, N. Kanazawa, J.H. Park, J.H. Han, Y. Matsui, N. Nagaosa, and Y. Tokura, Real-space observation of a two-dimensional skyrmion crystal, Nature (London) **465**, 901 (2010).
[14] T. Schulz, R. Ritz, A. Bauer, M. Halder, M. Wagner, C. Franz, C. Pfleiderer, K. Everschor, M. Garst, and A. Rosch, Emergent electrodynamics of skyrmions in a chiral magnet, Nature Phys. **8**, 301 (2012).
[15] J. Iwasaki, M. Mochizuki, and N. Nagaosa, Universal current-velocity relation of skyrmion motion in chiral magnets, Nature Commun. **4**, 1463 (2013).
[16] N. Nagaosa and Y. Tokura, Topological properties and dynamics of magnetic skyrmions, Nature Nanotechnol. **8**, 899 (2013).
[17] W. Jiang, P. Upadhyaya, W. Zhang, G. Yu, M.B. Jungfleisch, F.Y. Fradin, J.E. Pearson, Y. Tserkovnyak, K.L. Wang, O. Heinonen, S.G.E. te Velthuis, and A. Hoffmann, Blowing magnetic skyrmion bubbles, Science **349**, 283 (2015).
[18] S.-Z. Lin, C. Reichhardt, C.D. Batista, and A. Saxena, Particle model for skyrmions in metallic chiral magnets: Dynamics, pinning, and creep, Phys. Rev. B **87**, 214419 (2013).
[19] C. Reichhardt, D. Ray, and C.J. Olson Reichhardt, Collective transport properties of driven skyrmions with random disorder, Phys. Rev. Lett. **114**, 217202 (2015).
[20] J. Müller and A. Rosch, Capturing of a magnetic skyrmion with a hole, Phys. Rev. B **91**, 054410 (2015).
[21] C. Reichhardt, D. Ray, and C. J. Olson Reichhardt, Quantized transport for a skyrmion moving on a two-dimensional periodic substrate, Phys. Rev. B **91**, 104426 (2015).
[22] W. Jiang, X. Zhang, G. Yu, W. Zhang, M.B. Jungfleisch, J.E. Pearson, O. Heinonen, K.L. Wang, Y. Zhou, A. Hoffmann, and S.G.E. te Velthuis, Direct observation of the skyrmion Hall effect, arXiv:1603.07393 (unpublished).
[23] C. Reichhardt and C.J. Olson Reichhardt, Shapiro steps for skyrmion motion on a washboard potential with longitudinal and transverse ac drives, Phys. Rev. B **92**, 224432 (2015).
[24] P. Reimann, R. Kawai, C. Van den Broeck, and P. Hänggi, Coupled Brownian motors: Anomalous hysteresis and zero-bias negative conductance, Europhys. Lett. **45**, 545 (1999).
[25] R. Eichhorn, P. Reimann, and P. Hänggi, Brownian motion exhibiting absolute negative mobility, Phys. Rev. Lett. **88**, 190601 (2002).
[26] A. Ros, R. Eichhorn, J. Regtmeier, T.T. Duong, P. Reimann, and D. Anselmetti, Brownian motion: Absolute negative particle mobility, Nature (London) **436**, 928 (2005).
[27] C. Reichhardt and C. J. Olson Reichhardt, Absolute transverse mobility and ratchet effect on periodic two-dimensional symmetric substrates, Phys. Rev. E **68**, 046102 (2003).
[28] A. Fert, V. Cros, and J. Sampaio, Skyrmions on the track, Nature Nanotechnol. **8**, 152 (2013).
[29] C. Reichhardt, D. Ray, and C.J. Olson Reichhardt, Magnus-induced ratchet effects for skyrmions interacting with asymmetric substrates, New J. Phys. **17**, 073034 (2015).
[30] A. Barone and G. Paterno, *Physics and Applications of the Josephson Effect* (Wiley, New York, 1982).